



TerraFlow® Mill Test Report

Month of Issue: MAY 2021

Plant: Seattle, Washington
Product: TerraFlow 75
Manufactured: APRIL 2021
Mill Test Report Number: TerraFlow75_MAY 2021

ASTM C 1157 Standard Requirements

| CHEMICAL ANALYSIS | | | PHYSICAL ANALYSIS | | |
|-------------------|------------|-------------|----------------------------|------------|-------------|
| Item | Spec limit | Test Result | Item | Spec limit | Test Result |
| Slag, % | --- | 75 | Passing 325 Sieve (%) | --- | 95.2 |
| Type II, % | --- | 25 | Autoclave expansion (%) | 0.8 | -0.03 |
| | | | Compressive strength (MPa) | | |
| | | | 3 days | 5.0 min | 16.9 |
| | | | 7 days | 11.0 min | 28.3 |
| | | | 28 days | -- | 39.8 |

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of applicable Specifications for Type MH

Seattle Plant
5400 W. Marginal Way SW, Seattle, WA 98106
Phone: 206-937-8025

Certified By:

Daniel Waldron - QC Laboratory Supervisor

May 10, 2021