

## **Cement Mill Test Report**

Date of Issue: October 15, 2021

Plant: Exshaw AB

Product: Portland Cement Type I/II/V

Mill Test Report Number: MTR-I/II/V-2021-09
Manufactured: September 1-30, 2021

## ASTM C 150-20 and AASHTO M 85-18 Standard Requirements

CHEMICAL ANALYSIS			PHYSICAL ANALYSIS			
Item	Spec limit	Test Result	Item	Spec limit	Test Result	
Rapid Method, X-Ray (C114)			Air content of mortar (%) (C185)	12 max	6	
SiO <sub>2</sub> (%)		19.7				
Al <sub>2</sub> O <sub>3</sub> (%)	6.0 max	3.9	Blaine Fineness (m²/kg) (C204)	260 min	426	
Fe <sub>2</sub> O <sub>3</sub> (%)	6.0 max	3.6				
CaO (%)		62.2	Passing 45 μm (%) (C430)		99.2	
MgO (%)	6.0 max	4.4				
SO <sub>3</sub> (%)	2.3 max *	2.9	Autoclave Expansion (%) (C151)**	0.80 max	80.0	
Loss on Ignition (%)	3.5 max	2.4				
Insoluble Residue (%)	1.5 max	0.33	Compressive strength (MPa, [psi]) (C 109)			
CO <sub>2</sub> (%)		1.6				
Limestone (%)	5.0 max	3.9	3 days	12.0 [1740] min	29.6 [4300]	
CaCO <sub>3</sub> in Limestone (%)	70 min	96	7 days	19.0 [2760] min	34.9 [5070]	
Inorganic Process Addition	5.0 max	-	28 days (Reflects previous month's data)		42.2 [6130]	
(Lafarge Cement Kiln Dust)						
			Time of setting (minutes)			
Adjusted Potential Phase Composition (C 50)			Vicat Initial (C191)	45 - 375	104	
C₃S (%)		57				
C <sub>2</sub> S (%)		14				
C <sub>3</sub> A (%)	5 max	4				
C <sub>4</sub> AF (%)		11	Sulfate Resistance (%) (C452)**	0.040 max	0.035	
$C_4AF + 2(C_3A)$	25 max	19	Mortar Bar Expansion (%) (C1038)**	0.020 max	0.008	
C <sub>3</sub> S+4.75*C <sub>3</sub> A (%)	100 max	76				
ASTM C 150-17 and AASHTO M 85-17 Optional Requirements:						
NaEq (%)	0.60 max	0.56	False set (%) (C451)	50 min	90	

May exceed the SO<sub>3</sub> maximum based on C 1038 results of <0.020% expansion at 14 days.

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of ASTM C 150-20 & AASHTO M 85-18 STANDARD SPECIFICATIONS FOR TYPES I, II & V CEMENTS; and ASTM C 150-20 & AASHTO M 85-18 OPTIONAL CHEMICAL REQUIREMENTS FOR TYPES I, II & V LOW ALKALI CEMENT.

Certified By:

Western Canada BU - Exshaw Plant P.O. Box 160, Highway 1A, Exshaw AB, T0L 2C0

Phone: 403-673-3815

Lorraine Richards

Lorraine Richards Quality Control Coordinator

<sup>\*\*</sup> Current Production run not available - most recent provided



# **Cement Mill Test Report**

Date of Issue: October 15, 2021

Plant: Exshaw AB

Product: Portland Cement Type I/II/V

Mill Test Report Number: MTR-I/II/V-2020-09
Manufactured: September 1-30, 2021

## ASTM C 150-20 and AASHTO M 85-18 Standard Requirements

## **Additional Data**

Item		Test Result		
	Limestone	Inorganic Process Addition		
		Lafarge Cement Kiln Dust		
Amount (%)	3.9	-		
SiO <sub>2</sub> (%)	1.4	n/a		
Al <sub>2</sub> O <sub>3</sub> (%)	0.7	n/a		
Fe <sub>2</sub> O <sub>3</sub> (%)	0.3	n/a		
CaO (%)	52.4	n/a		
SO <sub>3</sub> (%)	0.2	n/a		
CO <sub>2</sub> (%)	42.2	n/a		

## **Base Cement Phase Composition**

Item	Test Result
C <sub>3</sub> S (%)	59
C <sub>2</sub> S (%)	14
C <sub>3</sub> A (%)	4
C <sub>4</sub> AF (%)	11

We certify that the data above reflects the materials used in cement manufacture during the production period indicated.

Note: Specifc Gravity for Portland Cements is 3.14

Certified By:

Western Canada BU - Exshaw Plant

Lorraine Richards

Lorraine Richards Quality Control Coordinator

P.O. Box 160, Highway 1A, Exshaw AB, T0L 2C0

Phone: 403-673-3815