



Cement Mill Test Report

Month of Issue: OCTOBER 2022

Plant: Product: Mill Test Report # Manufactured:

Richmond, British Columbia Portland Cement Type IL(15) MS R-TIL-22-10 SEPTEMBER 2022

ASTM C595 - 21 Standard Requirements

| CHEMICAL ANALYSIS | | | PHYSICAL ANALYSIS | | | |
|---|------------|-----------------------|--|-----------------|-----------|------|
| Item | Spec limit | Test Result | Item | Spec limit | Test Resu | lt |
| Rapid Method, X-Ray (C 114) | | | Air content of mortar (%) (C 185) | 12 max | 5.9 | |
| SiO2 (%) | | 18.4 | | | | |
| AI2O3 (%) | | 4.4 | Blaine Fineness (m2/kg) (C 204) | | 449 | |
| Fe2O3 (%) | | 3.0 | | | | |
| CaO (%) | | 63.4 | Passing 325 (%) (C 430) | | 98.9 | |
| MgO (%) | | 0.7 | | | | |
| SO3 (%) | 3.0 max* | 2.7 | Autoclave expansion (%) (C 151) | [-0.2 - 0.8] | 0.05 | |
| Loss on ignition @ 950 (%) | 10.0 max | 6.4 | | | | |
| NaEq (Alkali) (%) | | 0.48 | Compressive strength (Mpa [PSI]) (C 109) | | | |
| Insoluble residue (%) | | 0.43 | | | Мра | PSI |
| | | | 3 days | 13.0 [1890] min | 28.7 | 4150 |
| | | | 7 days | 20.0 [2900] min | 35.9 | 5200 |
| | | | 28 days (Reflects previous month's data) | 25.0 [3620] min | 45.6 | 6610 |
| | | | Time of setting (minutes) | | | |
| Adjusted Potential Phase Composition*** | | Vicat Initial (C 191) | 45-420 | 109 | | |
| C3S (%) | | 50 | . , | | | |
| C2S (%) | | 15 | Mortar Bar Expansion (C 1038)* | | | |
| C3A (%) | | 7 | 14 days, % max | 0.020 max | 0.005 | |
| C4AF (%) | | 9 | - | | | |
| . / | | | Cement Density (C186) | | 3.09 | |

* May exceed 3.0% SO3 maximum based on our C 1038 results of <0.02% expansion at 14 days. Cement meets ASTM C 1157 Type MS

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of: ASTM C 595-21 & AASHTO M 240-21 STANDARD SPECIFICATIONS FOR TYPE IL(15), TYPE IL(15) MS CEMENT

Cement complies with NSF 61

Western BU - Richmond 7611 No 9 Rd Richmond, BC 604 244 4300 Questions or enquiries can be directed to Rob Shogren Rob Shogren, PhD Lafarge - Technical Director 5400 W Marginal Way SW, Seattle WA P +1 206 923 9953 E Rob.Shogren@lafargeholcim.com Certified By:

dy Ń

Robyn van Zutphen Quality Supervisor 10/13/2022