

Cement Mill Test Report

Date of Issue: March 13, 2023

Plant: Exshaw, AB

Product: Portland Cement Type III

Mill Test Report Number: MTR-III-2023-02
Manufactured: February 1-28, 2023

ASTM C 150-21 and AASHTO M 85-18 Standard Requirements

CHEMICAL ANALYSIS PHYSICAL ANALYSIS

						-
Item	Spec limit	Test Result	Item	Spec limit	Test Re	sult
Rapid Method, X-Ray (C114))		Air content of Mortar (%) (C185)	12 max	6	
SiO ₂ (%)		19.2				
Al ₂ O ₃ (%)		4.0	Blaine Fineness (m ² /kg) (C204)		524	
Fe ₂ O ₃ (%)		3.5				
CaO (%)		61.9	Passing 45 μm (%) (C430)		99.5	
MgO (%)	6.0 max	4.7				
SO ₃ (%)	3.5 max	3.3	Autoclave Expansion (%) (C151)**	0.80 max	0.13	
Loss on Ignition (%)	3.5 max	2.4				
Insoluble Residue (%)*	1.5 max	0.37	Compressive strength (MPa, [psi]) (C109)			
CO ₂ (%)		1.8	1 day	12.0 [1740] min	26.3	[3820]
Limestone (%)	5.0 max	4.3	3 days	24.0 [3480] min	36.8	[5340]
CaCO ₃ in Limestone (%)	70 min	90.1	28 days (Reflects previous month's data)		52.1	[7550]
Inorganic Process Addition	5.0 max	-				
(Lafarge Cement Kiln Dust)						
			Time of setting (minutes)			
Adjusted Potential Phase Composition (C150)			Vicat Initial (C191)	45 - 375	79	
C ₃ S (%)		57				
C ₂ S (%)		12	Mortar Expansion (%) (C1038)	0.02 max	0.010	
C ₃ A (%)	15 max	5				
C₄AF (%)		11				

ASTM C 150-17 and AASHTO M 85-17 Optional Chemical Requirements: NaEq (%) 0.60 max 0.56

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of ASTM C 150-21 & AASHTO M 85-18 STANDARD SPECIFICATIONS FOR TYPE III CEMENT; and ASTM C 150-21 & AASHTO M 85-18 OPTIONAL CHEMICAL REQUIREMENTS FOR TYPE III LOW ALKALI CEMENT.



Our laboratory is AASHTO accredited. Grey highlighted tests are not within current Scope of Accrediation.



Western Canada BU - Exshaw Plant P.O. Box 160, Highway 1A, Exshaw AB, TOL 2C0

Phone: 403-673-3815

Certified By:

Lorraine Johnson

Lorraine Johnson Quality Manager



Cement Mill Test Report

Date of Issue: March 13, 2023

Plant: Exshaw, AB

Product: Portland Cement Type III

Mill Test Report Number: MTR-III-2023-02
Manufactured: February 1-28, 2023

ASTM C 150-21 and AASHTO M 85-18 Standard Requirements

Additional Data

Item	Test Result		
	Limestone	Inorganic Process Addition	
		Lafarge Cement Kiln Dust	
Amount (%)	4.3	-	
SiO ₂ (%)	1.5	n/a	
Al ₂ O ₃ (%)	0.7	n/a	
Fe ₂ O ₃ (%)	0.3	n/a	
CaO (%)	50.3	n/a	
SO ₃ (%)	0.3	n/a	
CO ₂ (%)	42.7	n/a	

Base Cement Phase Composition

Item	Test Result		
C ₃ S (%)	60		
C ₂ S (%)	12		
C ₃ A (%)	5		
C ₄ AF (%)	11		

We certify that the data above reflects the materials used in cement manufacture during the production period indicated.

Note: Specifc Gravity for Portland Cements is 3.15

Certified By:

Lorraine Johnson

Lorraine Johnson

Lorraine Johnson Quality Manager

Western Canada BU - Exshaw Plant P.O. Box 160, Highway 1A, Exshaw AB, TOL 2C0

Phone: 403-673-3815