

Cement Mill Test Report

Date of Issue: April 12, 2023

Plant: Exshaw, AB

Product: Portland Cement Type HE

Manufactured: March 1-31, 2023

| CHEMICAL ANALYSIS | | | PHYSICAL ANALYSIS | | |
|-----------------------------|-------------------|-------------|-------------------------------------|------------|-------------|
| Item | Spec limit | Test Result | Item | Spec limit | Test Result |
| Rapid Method, X-Ray | | | | | |
| SiO2 (%) | | 19.3 | | | |
| Al2O3 (%) | | 4.0 | Blaine Fineness (m2/kg) | | 518 |
| Fe2O3 (%) | | 3.5 | | | |
| CaO (%) | | 62.1 | Retained 45 um (%) | | 0.7 |
| MgO (%) | 5.0 max | 4.7 | | | |
| SO3 (%) | 3.5 max ** | 3.2 | Autoclave expansion (%)* | 1.0 max | 0.11 |
| Loss on ignition @ 950 (%) | 3.0 (3.5) max *** | 2.6 | | | |
| Loss on ignition @ 550(%) | 3.0 max | 0.6 | Compressive strength (MPa) | | |
| Insoluble residue (%)* | 1.5 max | 0.3 | 1 day | 13.5 min | 24.3 |
| | | | 3 day | 24.0 min | 34.4 |
| | | | 28 day (February 2023 Results) | | 50.5 |
| Inorganic Process Addition | 5.0 max | - | | | |
| (Cement Kiln Dust) | | | Time of setting (minutes) | | |
| | | | Vicat Initial | 45 - 375 | 80 |
| Potential Phase Composition | 1 | | | | |
| C3S (%) | | 65 | Mortar Bar Expansion (%) (C5)* | 0.020 max | 0.010 |
| C2S (%) | | 6 | | | |
| C3A (%) | | 5 | Colour (For Information Purposes Or | nly) | 31 |
| C4AF (%) | | 11 | | | |
| | | | | | |

Other Chemical Information:

NaEq (%) 0.58

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of the applicable specification for Type HE.



CSA A3001-18 STANDARD SPECIFICATIONS FOR TYPE HE CEMENT.

Lafarge Canada Inc. - Exshaw Plant P.O. Box 160, Highway 1A, Exshaw AB TOL 2C0

Phone: 403-673-3815

Certified By:

Lorraine Johnson

Lorraine Johnson Quality Manager

^{*} Latest available value

^{**} May exceed 3.5% SO3 maximum based on our A3004-C5 results of <0.020% expansion at 14 days.

^{***} May exceed 3.0% LOI maximum based on our LOI at 550C <3.0%.