

# **Cement Mill Test Report**

Date of Issue: August 08, 2023

Plant: Exshaw AB

Product: Portland Cement Type I/II/V

Mill Test Report Number: MTR-I/II/V-2023-07

Manufactured during the month of: July 2023

### ASTM C 150-20 and AASHTO M 85-18 Standard Requirements

CHEMICAL ANALYSIS			PHYSICAL ANALYSIS			
Item	Spec limit	Test Result	Item	Spec limit	Test Result	
Rapid Method, X-Ray (C114)			Air content of mortar (%) (C185)	12 max	6	
SiO <sub>2</sub> (%)		19.3				
Al <sub>2</sub> O <sub>3</sub> (%)	6.0 max	3.8	Blaine Fineness (m <sup>2</sup> /kg) (C204)	260 min	392	
Fe <sub>2</sub> O <sub>3</sub> (%)	6.0 max	3.4				
CaO (%)		61.9	Passing 45 μm (%) (C430)		97.8	
MgO (%)	6.0 max	4.7				
SO <sub>3</sub> (%)	2.3 max *	3.0	Autoclave Expansion (%) (C151)**	0.80 max		
Loss on Ignition (%)	3.5 max	2.8				
Insoluble Residue (%)	1.5 max		Compressive strength (MPa, [psi]) (C 10	19)		
CO <sub>2</sub> (%)		1.9				
Limestone (%)	5.0 max	4.5	3 days	12.0 [1740] min	28.6 [4142]	
CaCO <sub>3</sub> in Limestone (%)	70 min	96	7 days	19.0 [2760] min	34.8 [5043]	
Inorganic Process Addition (Lafarge Cement Kiln Dust)	5.0 max		28 days (Previous Month Results)		44.5 [6459]	
			Time of setting (minutes)			
Adjusted Potential Phase Co	mposition (C 50)		Vicat Initial (C191)	45 - 375	101	
C <sub>3</sub> S (%)		58				
C <sub>2</sub> S (%)		12				
C <sub>3</sub> A (%)	5 max	4				
C₄AF (%)		10	Sulfate Resistance (%) (C452)**	0.040 max	0.026	
C <sub>4</sub> AF + 2(C <sub>3</sub> A)	25 max	77	Mortar Bar Expansion (%) (C1038) **	0.020 max	0.014	
C <sub>3</sub> S+4.75*C <sub>3</sub> A (%)	100 max	18				
ASTM C 150-17 and AASHTC	M 85-17 Optiona	I Requirements:				
NaEq (%)	0.60 max	0.56	False set (%) (C451)	50 min	74	

 $<sup>^{\</sup>star}$  May exceed the SO $_{\!3}$  maximum  $\,$  based on C 1038 results of <0.020% expansion at 14 days.

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of ASTM C 150-20 & AASHTO M 85-18 STANDARD SPECIFICATIONS FOR TYPES I, II & V CEMENTS; and ASTM C 150-20 & AASHTO M 85-18 OPTIONAL CHEMICAL REQUIREMENTS FOR TYPES I, II & V LOW ALKALI CEMENT.

Western Canada BU - Exshaw Plant P.O. Box 160, Highway 1A, Exshaw AB, T0L 2C0

Phone: 403-673-3815

Certified By:

John W Blair Quality Manager

<sup>\*\*</sup> Current Production run not available - most recent provided



## **Cement Mill Test Report**

Date of Issue: August 08, 2023

Plant: Exshaw AB

Product: Portland Cement Type I/II/V

Mill Test Report Number: MTR-I/II/V-2023-07

Manufactured: July 2023

### ASTM C 150-20 and AASHTO M 85-18 Standard Requirements

#### **Additional Data**

Item	Test Result		
	Limestone	Inorganic Process Addition	
		Lafarge Cement Kiln Dust	
Amount (%)	4.5	-	
SiO <sub>2</sub> (%)	1.7	n/a	
Al <sub>2</sub> O <sub>3</sub> (%)	0.4	n/a	
Fe <sub>2</sub> O <sub>3</sub> (%)	0.2	n/a	
CaO (%)	50.1	n/a	
SO <sub>3</sub> (%)	0.1	n/a	
CO <sub>2</sub> (%)	42.5	n/a	

#### **Base Cement Phase Composition**

Item	Test Result	
C <sub>3</sub> S (%)	60	
C <sub>2</sub> S (%)	12	
C <sub>3</sub> A (%)	4	
C₄AF (%)	11	

We certify that the data above reflects the materials used in cement manufacture during the production period indicated.

Note: Specifc Gravity for Portland Cements is 3.14

Western Canada BU - Exshaw Plant P.O. Box 160, Highway 1A, Exshaw AB, TOL 2C0

Phone: 403-673-3815

Certified By:

John W Blair Quality Manager