

Cement Mill Test Report

Date of Issue: January 10, 2024

Plant: **Exshaw AB Product:** OneCem

Mill Test Report Number: MTR-IL-2023-12 Manufactured during the month of: December 2023

CHEMICAL ANALYSIS PHYSICAL ANALYSIS Spec limit **Test Result** Spec limit Test Result Item ltem Rapid Method, X-Ray (C114) Blaine Fineness (m²/kg) (C204) 17.3 SiO₂ (%) Passing 45 µm (%) (C430) Al₂O₃ (%) 3.5 99.4 Fe₂O₃ (%) 3.1 Air Content (%) (C186) CaO (%) 60.3 12 max 6 MgO (%) 4.4 3.3 3.0 max* Compressive Strength (MPa [psi]) (C109) SO₃ (%) K₂O (%) 0.57 1 day 20.0 [2898] Na₂O (%) 0.14 3 days 13.0 [1890] min 32.5 [4706] NaEq (%) 0.51 7 days 20.0 [2900] min 38.3 [5551] Loss on Ignition @ 950 (%) 10.0 max 25.0 [3620] min 6.6 28 days (Previous Month Results) 43.9 [6366] Loss on Ignition @ 550 (%) 8.0 **Inorganic Process Addition** 5.0 max Time of setting (minutes) (C191) Vicat Initial (Lafarge Cement Kiln Dust) 45 min. 106 Adjusted Potential Phase Composition (C 150 - For information only) ASTM C1012 Expansion %, (6 months)*** 0.05 C3S (%) C2S (%) Mortar Bar Expansion (%) (C1038)** 0.020 max 0.010 9 C₃A (%) C₄AF (%) 9

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of ASTM C595/C595M-23 & AASHTO M 240-23 STANDARD SPECIFICATIONS FOR TYPE IL (13) and (HS) CEMENT.

Exceptions: ASTM C1012 and C1038 are not within the current Scope of Accrediation.

Western BU - Exshaw Plant

P.O. Box 160, Highway 1A, Exshaw AB T0L 2C0

Phone: 403-673-3815







Certified By:

John W Blair **Quality Manager**

^{*} May exceed the SO₃ maximum based on C1038 results of <0.020% expansion at 14 days.

^{**} Current Production run not available - most recent provided

^{***} Performed by Lafarge Edmonton and/or Seattle Labs



Cement Mill Test Report

Date of Issue: January 10, 2024

Plant: Exshaw AB Product: OneCem

Mill Test Report Number: MTR-IL-2023-12
Manufactured: December 2023

Additional Data - For information only.

Item	Test Result	Test Result
	Limestone	Inorganic Process Addition
		Lafarge Cement Kiln Dust
Amount (%)	13.6	-
SiO ₂ (%)	1.6	n/a
Al ₂ O ₃ (%)	0.4	n/a
Fe ₂ O ₃ (%)	0.2	n/a
CaO (%)	48.1	n/a
SO ₃ (%)	0.1	n/a
CO ₂ (%)	42.8	n/a

Base Cement Phase Composition - C150 - For information only.

Item	Test Result	
C ₃ S (%)	61	
C ₂ S (%)	11	
C ₃ A (%)	5	
C ₄ AF (%)	11	

Specific Gravity: 3.11

Western Canada BU - Exshaw Plant P.O. Box 160, Highway 1A, Exshaw AB, T0L 2C0

Phone: 403-673-3815

Certified By:

John W Blair Quality Manager