

# **Cement Mill Test Report**

Date of Issue: February 12, 2024

Plant: Exshaw AB

Product: Portland Cement Type I/II/V

Mill Test Report Number: MTR-I/II/V-2024-1
Manufactured during the month of: January 2024

### ASTM C 150-22 and AASHTO M 85-22 Standard Requirements

CHEMICAL ANALYSIS			PHYSICAL ANALYSIS		
Item	Spec limit	Test Result	Item	Spec limit	Test Result
Rapid Method, X-Ray (C114)			Air content of mortar (%) (C185)	12 max	5
SiO <sub>2</sub> (%)		19.3			
Al <sub>2</sub> O <sub>3</sub> (%)	6.0 max	3.9	Blaine Fineness (m <sup>2</sup> /kg) (C204)	260 min	426
Fe <sub>2</sub> O <sub>3</sub> (%)	6.0 max	3.6			
CaO (%)		61.8	Passing 45 μm (%) (C430)		98.5
MgO (%)	6.0 max	4.8			
SO <sub>3</sub> (%)	2.3 max *	2.9	Compressive strength (MPa, [psi]) (C 10	9)	
Loss on Ignition (%)	3.5 max	2.6			
Insoluble Residue (%)*	1.5 max	0.3	3 days	12.0 [1740] min	29.6 [4299]
CO <sub>2</sub> (%)		1.8	7 days	19.0 [2760] min	35.7 [5175]
Limestone (%)	5.0 max	4.3	28 days (Previous Month's Result)		48.0 [6959]
CaCO <sub>3</sub> in Limestone (%)	70 min	97.0			
Inorganic Process Addition	5.0 max		Time of setting (minutes)		
(Lafarge Cement Kiln Dust)			Vicat Initial <i>(C191)</i>	45 - 375	86
Adjusted Potential Phase Co	mposition <i>(C50)</i>				
C <sub>3</sub> S (%)		57	Sulfate Resistance (%) (C452)**	0.040 max	0.023
C <sub>2</sub> S (%)		12			
C <sub>3</sub> A (%)	5 max	4	Mortar Bar Expansion (%) (C1038) **	0.020 max	0.010
C <sub>4</sub> AF (%)		11			
$C_4AF + 2(C_3A)$	25 max	20			
C <sub>3</sub> S+4.75*C <sub>3</sub> A (%)	100 max	78			
ASTM C 150-17 and AASHTO M 85-17 Optional Requirements:					

NaEq (%) 0.60 max 0.58

\* May exceed the SO<sub>3</sub> maximum based on C 1038 results of <0.020% expansion at 14 days.

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of:

ASTM C 150-22 & AASHTO M 85-22 STANDARD SPECIFICATIONS FOR TYPES I, II & V CEMENTS; and ASTM C 150-22 & AASHTO M 85-22 OPTIONAL CHEMICAL REQUIREMENTS FOR TYPES I, II & V LOW ALKALI CEMENT. AASHTO Accrediation Exceptions: C452 and C1038

Western Canada BU - Exshaw Plant P.O. Box 160, Highway 1A, Exshaw AB, T0L 2C0 Phone: 403-673-3815 Certified By:

John W Blair Quality Manager

False set (%) (C451)

50 min

<sup>\*\*</sup> Latest available results.



# **Cement Mill Test Report**

Date of Issue: February 12, 2024

Plant: Exshaw AB

Product: Portland Cement Type I/II/V

Mill Test Report Number: MTR-I/II/V-2024-1 Manufactured: January 2024

### ASTM C 150-22 and AASHTO M 85-22 Standard Requirements

#### **Additional Data**

Item	Test Result		
	Limestone	Inorganic Process Addition	
		Lafarge Cement Kiln Dust	
Amount (%)	4.3	-	
SiO <sub>2</sub> (%)	1.6	n/a	
Al <sub>2</sub> O <sub>3</sub> (%)	0.4	n/a	
Fe <sub>2</sub> O <sub>3</sub> (%)	0.2	n/a	
CaO (%)	49.6	n/a	
SO <sub>3</sub> (%)	0.1	n/a	
CO <sub>2</sub> (%)	42.7	n/a	

#### **Base Cement Phase Composition**

Item	Test Result
C <sub>3</sub> S (%)	60
C <sub>2</sub> S (%)	12
C <sub>3</sub> A (%)	4
C₄AF (%)	11

We certify that the data above reflects the materials used in cement manufacture during the production period indicated.

Note: Specifc Gravity for Portland Cements is 3.14

Western Canada BU - Exshaw Plant P.O. Box 160, Highway 1A, Exshaw AB, T0L 2C0

Phone: 403-673-3815

Certified By:

John W Blair Quality Manager