



Cement Mill Test Report

Date of Issue: March 21, 2024

Plant: Exshaw, AB
 Product: Portland Cement Type III
 Mill Test Report Number: MTR-III-2024-2
 Manufactured during the month of: February 2024

ASTM C 150-22 and AASHTO M 85-22 Standard Requirements

CHEMICAL ANALYSIS			PHYSICAL ANALYSIS		
Item	Spec limit	Test Result	Item	Spec limit	Test Result
Rapid Method, X-Ray (C114)			Air content of mortar (%) (C185)		
SiO ₂ (%)	---	19.4		12 max	5
Al ₂ O ₃ (%)	---	3.8	Blaine Fineness (m²/kg) (C204)		
Fe ₂ O ₃ (%)	---	3.6		---	560
CaO (%)	---	61.8	Passing 45 µm (%) (C430)		
MgO (%)	6.0 max	4.8		---	99.5
SO ₃ (%) **	3.5 max	3.4	Compressive strength (MPa, [psi]) (C109)		
Loss on Ignition (%)	3.5 max	2.5	1 day	12.0 [1740] min	23.3 [3379]
Insoluble Residue (%)	1.5 max	0.6	3 days	24.0 [3480] min	35.0 [5077]
CO ₂ (%)	---	1.7	28 days (Previous Month's Result)		49.0 [7100]
Limestone (%)	5.0 max	4.2	Time of setting (minutes)		
CaCO ₃ in Limestone (%)	70 min	97.0	Vicat Initial (C191)	45 - 375	76
Inorganic Process Addition (Lafarge Cement Kiln Dust)	5.0 max		Mortar Bar Expansion (%) (C1038) *		
Adjusted Potential Phase Composition (C150)				0.020 max	0.011
C ₃ S (%)	---	56			
C ₂ S (%)	---	13			
C ₃ A (%)	15 max	4			
C ₄ AF (%)	---	11			

ASTM C 150-22 and AASHTO M 85-22 Optional Chemical Requirements:

NaEq (%) Weekly Averages: Week 1 Week 2 0.56 Week 3 0.58 Week 4 0.58 Max 0.60

* Latest available result.

** May exceed 3.0% SO₃ maximum based on C1038 results of <0.020% expansion at 14 days.

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of:

ASTM C 150-22 & AASHTO M 85-22 STANDARD SPECIFICATIONS FOR TYPE III CEMENT; and

ASTM C 150-22 & AASHTO M 85-22 OPTIONAL CHEMICAL REQUIREMENTS FOR TYPE III LOW ALKALI CEMENT.

Exceptions: C430 is excluded from the scope of the AASHTO accreditation.

Western Canada BU - Exshaw Plant
 P.O. Box 160, Highway 1A, Exshaw AB, T0L 2C0
 Phone: 403-673-3815

Certified By:


 John W Blair
 Quality Manager



Certified to
NSF/ANSI/CAN 61



AASHTO
ACCREDITED



Cement Mill Test Report

Date of Issue: March 21, 2024

Plant: Exshaw, AB
Product: Portland Cement Type III
Mill Test Report Number: MTR-III-2024-2
Manufactured: February 2024

ASTM C 150-22 and AASHTO M 85-22 Standard Requirements

Additional Data

Item	Test Result	
	Limestone	Inorganic Process Addition Lafarge Cement Kiln Dust
Amount (%)	4.1	-
SiO ₂ (%)	2.0	n/a
Al ₂ O ₃ (%)	0.5	n/a
Fe ₂ O ₃ (%)	0.2	n/a
CaO (%)	48.6	n/a
SO ₃ (%)	0.2	n/a
CO ₂ (%)	42.4	n/a

Base Cement Phase Composition

Item	Test Result
C ₃ S (%)	59
C ₂ S (%)	13
C ₃ A (%)	4
C ₄ AF (%)	11

We certify that the data above reflects the materials used in cement manufacture during the production period indicated.

Note: Specific Gravity for Portland Cements is 3.15

Western Canada BU - Exshaw Plant
P.O. Box 160, Highway 1A, Exshaw AB, T0L 2C0
Phone: 403-673-3815

Certified By:


John W Blair
Quality Manager