

Cement Mill Test Report

Date of Issue: April 11, 2024

Plant: **Exshaw AB**

Product: Portland Cement Type I/II Mill Test Report Number: **ESW Type I-II 2024-3**

Manufactured during the month of: March 2024

ASTM C 150-22 and AASHTO M 85-22 Standard Requirements

CHEMICAL ANALYSIS			PHYSICAL ANALYSIS		
Item	Spec limit	Test Result	Item	Spec limit	Test Result
Rapid Method, X-Ray (C114)			Air content of mortar (%) (C185)	12 max	6
SiO ₂ (%)		19.1			
Al ₂ O ₃ (%)	6.0 max	4.3	Blaine Fineness (m ² /kg) (C204)	260 min	470
Fe ₂ O ₃ (%)	6.0 max	3.1			
CaO (%)		62.1	Passing 45 μm (%) (C430)		98.4
MgO (%)	6.0 max	4.4			
SO ₃ (%)*	3.0 max *	3.0	Compressive strength (MPa, [psi]) (C 10	9)	
Loss on Ignition (%)	3.5 max	2.9			
Insoluble Residue (%)	1.5 max	0.3	3 days	12.0 [1740] min	28.7 [4157]
CO ₂ (%)		1.8	7 days	19.0 [2760] min	36.0 [5216]
Limestone (%)	5.0 max	4.2	28 days (Previous Month's Result)		40.8 [5921]
CaCO ₃ in Limestone (%)	70 min	97.0			
Inorganic Process Addition	5.0 max		Time of setting (minutes)		
(Lafarge Cement Kiln Dust)			Vicat Initial <i>(C191)</i>	45 - 375	59
Adjusted Potential Phase Composition (C50)			Mortar Bar Expansion (%) (C1038)**	0.020 max	0.014
C ₃ S (%)		58			
C ₂ S (%)		11			
C ₃ A (%)	5 max	6			
C ₄ AF (%)		9			
$C_4AF + 2(C_3A)$	25 max	21			
C ₃ S+4.75*C ₃ A (%)	100 max	87			

0.60 max False set (%) (C451) 85

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of:

ASTM C 150-22 & AASHTO M 85-22 STANDARD SPECIFICATIONS FOR TYPES I / II CEMENTS; and ASTM C 150-22 & AASHTO M 85-22 OPTIONAL CHEMICAL REQUIREMENTS FOR TYPES I / II LOW ALKALI CEMENT.

AASHTO Accrediation Exceptions: C430

Western Canada BU - Exshaw Plant P.O. Box 160, Highway 1A, Exshaw AB, T0L 2C0

Phone: 403-673-3815

Certified By:

John W Blair **Quality Manager**

^{*} May exceed the SO₃ maximum based on C 1038 results of <0.020% expansion at 14 days. ** Latest available results.



Cement Mill Test Report

Date of Issue: April 11, 2024

Plant: Exshaw AB

Product: Portland Cement Type I/II
Mill Test Report Number: ESW_Type I-II 2024-3

Manufactured: March 2024

ASTM C 150-22 and AASHTO M 85-22 Standard Requirements

Additional Data

Item	Test Result		
	Limestone	Inorganic Process Addition	
		Lafarge Cement Kiln Dust	
Amount (%)	4.2	-	
SiO ₂ (%)	1.5	n/a	
Al ₂ O ₃ (%)	0.4	n/a	
Fe ₂ O ₃ (%)	0.2	n/a	
CaO (%)	50.5	n/a	
SO ₃ (%)	0.1	n/a	
CO ₂ (%)	42.7	n/a	

Base Cement Phase Composition

Item	Test Result	
C ₃ S (%)	60	
C ₂ S (%)	11	
C ₃ A (%)	7	
C₄AF (%)	10	

We certify that the data above reflects the materials used in cement manufacture during the production period indicated.

Note: Specifc Gravity for Portland Cements is 3.14

Western Canada BU - Exshaw Plant P.O. Box 160, Highway 1A, Exshaw AB, T0L 2C0

Phone: 403-673-3815

Certified By:

John W Blair Quality Manager