

# **Cement Mill Test Report**

Date of Issue: April 11, 2024

Plant: Exshaw, AB

Product: Portland Cement Type III
Mill Test Report Number: ESW\_Type III 2024-3

Manufactured during the month of: March 2024

## ASTM C 150-22 and AASHTO M 85-22 Standard Requirements

**CHEMICAL ANALYSIS** PHYSICAL ANALYSIS Spec limit **Test Result** Spec limit Item ltem **Test Result** Rapid Method, X-Ray (C114) Air content of mortar (%) (C185) 12 max 6 SiO<sub>2</sub> (%) 192 Blaine Fineness (m<sup>2</sup>/kg) (C204) Al<sub>2</sub>O<sub>3</sub> (%) 4.2 566 Fe<sub>2</sub>O<sub>3</sub> (%) 3.2 CaO (%) 62.3 Passing 45 μm (%) (C430) 99.5 MgO (%) 6.0 max 4.5 Compressive strength (MPa, [psi]) (C109) SO<sub>3</sub> (%) \*\* 3.3 3.5 max Loss on Ignition (%) 2.5 12.0 [1740] min 25.4 [3676] 3.5 max 1 day 24.0 [3480] min Insoluble Residue (%) 1.5 max 0.3 3 days 35.9 [5209] CO<sub>2</sub> (%) 1.8 28 days (Previous Month's Result) 48.8 [7082] Limestone (%) 5.0 max 4.3 CaCO<sub>3</sub> in Limestone (%) 70 min 97.0 Inorganic Process Addition 5.0 max Time of setting (minutes) (Lafarge Cement Kiln Dust) Vicat Initial (C191) 45 - 375 56 Adjusted Potential Phase Composition (C150) Mortar Bar Expansion (%) (C1038) 0.020 max 0.011 C<sub>3</sub>S (%) 57 C2S (%) 12 C<sub>3</sub>A (%) 15 max 6 C<sub>4</sub>AF (%) 10

ASTM C 150-22 and AASHTO M 85-22 Optional Chemical Requirements:

Na<sub>2</sub>Oeq (%) Weekly Averages: Week 1 0.55 Week 2 0.58 Week 3 0.56 Week 4 0.56 Max 0.60

\*\* May exceed 3.0% SO3 maximum based on C1038 results of <0.020% expansion at 14 days.

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of:

ASTM C 150-22 & AASHTO M 85-22 STANDARD SPECIFICATIONS FOR TYPE III CEMENT; and ASTM C 150-22 & AASHTO M 85-22 OPTIONAL CHEMICAL REQUIREMENTS FOR TYPE III LOW ALKALI CEMENT.

Exceptions: C430 is excluded from the scope of the AASHTO accreditation.

Western Canada BU - Exshaw Plant P.O. Box 160, Highway 1A, Exshaw AB, T0L 2C0

Phone: 403-673-3815

Certified By:

John W Blair Quality Manager



# **Cement Mill Test Report**

Date of Issue: April 11, 2024

Plant: Exshaw, AB

Product: Portland Cement Type III
Mill Test Report Number: ESW\_Type III 2024-3

Manufactured: March 2024

# ASTM C 150-22 and AASHTO M 85-22 Standard Requirements

## **Additional Data**

Item	Test Result	
	Limestone	Inorganic Process Addition
		Lafarge Cement Kiln Dust
Amount (%)	4.3	-
SiO <sub>2</sub> (%)	1.7	n/a
Al <sub>2</sub> O <sub>3</sub> (%)	0.5	n/a
Fe <sub>2</sub> O <sub>3</sub> (%)	0.2	n/a
CaO (%)	50.5	n/a
SO <sub>3</sub> (%)	0.1	n/a
CO <sub>2</sub> (%)	42.5	n/a

## **Base Cement Phase Composition**

Item	Test Result
C <sub>3</sub> S (%)	60
C <sub>2</sub> S (%)	12
C <sub>3</sub> A (%)	6
C₄AF (%)	10

We certify that the data above reflects the materials used in cement manufacture during the production period indicated.

Note: Specifc Gravity for Portland Cements is 3.15

Western Canada BU - Exshaw Plant P.O. Box 160, Highway 1A, Exshaw AB, T0L 2C0

Phone: 403-673-3815

Certified By:

John W Blair Quality Manager