

Cement Mill Test Report

Month of Issue: April 2024

Plant: **Richmond, British Columbia**
 Product: **OneCem**
 Mill Test Report #: **R-TIL-24-04**
 Manufactured: **March 2024**

ASTM C595 - 21 Standard Requirements

CHEMICAL ANALYSIS			PHYSICAL ANALYSIS		
Item	Spec limit	Test Result	Item	Spec limit	Test Result
Rapid Method, X-Ray (C 114)			Air content of mortar (%) (C 185)	12 max	6.1
SiO ₂ (%)	---	18.4	Blaine Fineness (m ² /kg)	---	455
Al ₂ O ₃ (%)	---	4.6	Passing 325 (%)	---	99.0
Fe ₂ O ₃ (%)	---	3.0	Compressive strength (Mpa [PSI]) (C 109)		
CaO (%)	---	62.7			
MgO (%)	---	1.0			
SO ₃ (%)	3.0 max*	2.7			
Loss on ignition @ 950 (%)	10.0 max	6.7			
NaEq (Alkali) (%)	---	0.42	3 days	13.0 min	Mpa 30.1 PSI 4360
Insoluble residue (%)	---	0.39	7 days	20.0 min	37.4 5420
				25.0 min	44.3 6430
			28 days (Reflects previous month's data)		
Inorganic Process Addition (%)		3	Time of setting (minutes)		
			Vicat Initial (C 191)	45-420	115
Adjusted Potential Phase Composition**			Mortar Bar Expansion (C 1038)*		
C3S (%)	---	44	14 days, % max	0.020 max	0.001
C2S (%)	---	19	Cement Density (C186)		3.09
C3A (%)	---	7			
C4AF (%)	---	9			
Sulphate Resistance C1012 (Q2/2023)		0.10 max 0.092			
Sulphate Resistance ASTM C-452 (Q1/2024)		0.05 max 0.04			

* May exceed 3.0% SO₃ maximum based on our C 1038 results of <0.02% expansion at 14 days.

** Corrected by using ASTM Calculation for Limestone Cement


We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of:
 ASTM C 595-21 & AASHTO M 240-21 STANDARD SPECIFICATIONS FOR TYPE IL(15), TYPE IL(15) MS CEMENT

Cement complies with NSF 61

Western BU - Richmond
 7611 No 9 Rd Richmond, BC
 604 244 4300

Questions or enquiries can be directed to Rob Shogren
 Rob Shogren, PhD
 Lafarge - Technical Director
 5400 W Marginal Way SW, Seattle WA
 P +1 206 923 9953
 E Rob.Shogren@lafargeholcim.com

Certified By:



Robyn van Zutphen
 Quality Manager
 4/19/2024