

Cement Mill Test Report

Date of Issue: August 13, 2024

Plant: Exshaw, AB

Product: Portland Cement Type III
Mill Test Report Number: ESW_Type III 2024-7

Manufactured during the month of: July 2024

ASTM C 150-22 and AASHTO M 85-22 Standard Requirements

CHEMICAL ANALYSIS PHYSICAL ANALYSIS Spec limit **Test Result** Spec limit ltem **Test Result** Rapid Method, X-Ray (C114) Air content of mortar (%) (C185) 12 max 6 SiO₂ (%) 193 Blaine Fineness (m²/kg) (C204) Al₂O₃ (%) 4.2 493 Fe₂O₃ (%) 3.3 CaO (%) 61.9 Passing 45 μm (%) (C430) 99.4 MgO (%) 6.0 max 4.6 Compressive strength (MPa, [psi]) (C109) SO₃ (%) ** 3.5 max 3.4 Loss on Ignition (%) 12.0 [1740] min 20.8 [3023] 3.5 max 2.4 1 day 24.0 [3480] min Insoluble Residue (%) 1.5 max 0.3 3 days 33.2 [4810] CO₂ (%) 1.8 28 days (Previous Month's Result) 48.2 [6985] Limestone (%) 5.0 max 4.2 CaCO₃ in Limestone (%) 70 min 96.0 Inorganic Process Addition 5.0 max Time of setting (minutes) (Lafarge Cement Kiln Dust) Vicat Initial (C191) 45 - 375 65 Adjusted Potential Phase Composition (C150) Mortar Bar Expansion (%) (C1038) 0.020 max 0.005 C₃S (%) 55 C2S (%) 14 C₃A (%) 15 max 6 C₄AF (%) 10

ASTM C 150-22 and AASHTO M 85-22 Optional Chemical Requirements:

Na₂Oeq (%) Weekly Averages: Week 1 0.54 Week 2 0.49 Week 3 0.50 Week 4 0.50 Max 0.60

** May exceed 3.0% SO3 maximum based on C1038 results of <0.020% expansion at 14 days.

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of:

ASTM C 150-22 & AASHTO M 85-22 STANDARD SPECIFICATIONS FOR TYPE III CEMENT; and ASTM C 150-22 & AASHTO M 85-22 OPTIONAL CHEMICAL REQUIREMENTS FOR TYPE III LOW ALKALI CEMENT.

Exceptions: C430 is excluded from the scope of the AASHTO accreditation.

Western Canada BU - Exshaw Plant P.O. Box 160, Highway 1A, Exshaw AB, T0L 2C0

Phone: 403-673-3815

Certified By:

John W Blair Quality Manager



Cement Mill Test Report

Date of Issue: August 13, 2024

Plant: Exshaw, AB

Product: Portland Cement Type III
Mill Test Report Number: ESW_Type III 2024-7

Manufactured: July 2024

ASTM C 150-22 and AASHTO M 85-22 Standard Requirements

Additional Data

Item	Test Result	
	Limestone	Inorganic Process Addition
		Lafarge Cement Kiln Dust
Amount (%)	4.2	-
SiO ₂ (%)	2.1	n/a
Al ₂ O ₃ (%)	0.5	n/a
Fe ₂ O ₃ (%)	0.2	n/a
CaO (%)	49.9	n/a
SO ₃ (%)	0.1	n/a
CO ₂ (%)	42.3	n/a

Base Cement Phase Composition

Item	Test Result
C ₃ S (%)	57
C ₂ S (%)	15
C₃A (%)	6
C₄AF (%)	10

Specific Gravity (For Information Purposes Only) 3.17

We certify that the data above reflects the materials used in cement manufacture during the production period indicated.

Western Canada BU - Exshaw Plant P.O. Box 160, Highway 1A, Exshaw AB, T0L 2C0

Phone: 403-673-3815

Certified By:

John W Blair Quality Manager