

Cement

FLY ASH TEST REPORT

Analysis by: Lafarge Seattle Concrete Lab

Sample from : Centralia Power Plant

Average Analysis: December 2024
Test Report Number 1-25 F CSA

Chemical Analysis

		Limits
Silicon Dioxide (SiO ₂)	51.8 %	
Aluminum Oxide (Al ₂ O ₃)	18.0 %	
Iron Oxide (Fe ₂ O ₃)	6.0 %	
Sulphur Trioxide (SO ₃)	0.9 %	
Calcium Oxide (CaO)	13.6 %	15% Max - CSA
Magnesium Oxide	4.0 %	
Moisture Content	0.18 %	
Loss on Ignition	0.36 %	
Total Alkalies as Equivalent Na ₂ O	4.27 %	

Physical Analysis

Fineness Retained on 45 um (No. 325 Sieve)	14.3	%	34% Max - CSA
Strength Activity Index with Portland Cement			
% of Control at 28 Days (previous month's result)	100	%	
Water Requirement, Percent of Control	91	%	
Density	2.60	Mg/m ³	

We hereby certify that the composite fly ash sample above meets the chemical and physical requirements of CAN/CSA A3001 for Type F Fly Ash.

Certified :

Rob Shogren Technical Director

WESTERN REGION

5400 West Marginal Way SW, Seattle, Washington 98106-1517 Office: 206.923.0098 or 800.477.0100 Fax: 206.923.0388