

Mill Test Report Number: SEA_NEWCEM_December2024 YEAR: 2024 MONTH OF PRODUCTION: November PLANT: Seattle CEMENT TYPE: NewCem Grade 100

Reference Cement			Slag		
Fineness by Air Permeability (m²/kg; ASTM C204)	381		Fineness by Air Permeability (m ² /kg; ASTM C204)	492	
Fineness by 45 μm (No. 325) Sieve (% retain; ASTM C430)	3.3		Fineness by 45 μm (No. 325) Sieve (% retain; ASTM C430)	4.5	
Compressive Strength (ASTM C109/C109 M) 7-day 28-day	psi 4,780 5,840	<u>Min Limit</u> - 5,000	Compressive Strength (ASTM C109/C109 M)	<u>SAI</u>	SAI Limit <u>Min</u>
	Actual	<u>Limits</u>	28-day (Previous Month)	100	95
Total Alkalies (Na ₂ O + 0.658 K ₂ O) (%, ASTM C114)	0.88	0.6-0.9	Specific Gravity (Mg/m ³ ; ASTM C188)	2.87	
				Actual	Max Limit
CHEMICAL ANALYSIS Silica Dioxide (SiO ₂ , ASTM C114)		Percent 31.9	Air Content of Mortar (%, ASTM C185)	5	12
Ferric Oxide (Fe ₂ O _{3;} ASTM C114) Aluminum Oxide (Al ₂ O ₃ ; ASTM C114)		1.4 12	Sulfide Sulfur (% S, ASTM C114)	0.8	2.5
Calcium Oxide (CaO; ASTM C114) Sulfur Trioxide (SO ₃ ; ASTM C114)		40.6 7	Sulfate Ion	6.2	А
Magnesium Oxide (MgO; ASTM C114) Loss on Ignition (L.O.I.; ASTM C114)		4.3 1.90	(% as SO3, ASTM C114)		
Total Alkalies Inorganic Process Addition		0.68 8.5	Sulfate Expansion (% Expansion, ASTM C1038, CSA C5)	0.002	0.020
Antonio			Color Value L*	78.8	

A Not Applicable.

The ground granulated blast furnace slag complies with the current specification of the chemical physical requirement of ASTM C-989, AASHTO M-302 for grade 100 Ground Granulated Blast Furace Slag (GGBFS) and and CSA A3001 Slag.

Slag source is JFE Mineral Company in Kurashiki City, Japan. NewCem is ground and manufactured in Seattle, WA.



Certified by: het J. Shagen Rob Shogren

Technical Director December 5, 2024